

# Paged Softwood ThinPly



The mark of responsible forestry

Paged Softwood ThinPly is made of standard thickness locally sourced Polish pine and offers its users high durability and resistance to mould and UV lightening. Thanks to its high load-bearing capacity, smooth and uniform surface Paged Softwood ThinPly is widely used in construction and packaging industries.

### KEY BENEFITS AND APPLICATIONS

- Main application areas include: construction, wall sheeting, panelling, furniture joinery, packaging
- Made from highly regarded „Pinus Sylvestris” wood
- Good protection against fungi and moisture
- Made from responsibly sourced wood in Poland

### STANDARD SIZES\*[mm]

2500x1250/1500  
1500x3000

\*Other formats available on request

### NOMINAL THICKNESS WITH STANDARD DEVIATION, NUMBER OF PLYS, DENSITY AS PER EN 315, EN 323 & EN 324

Nominal Thickness (mm)*	Number of plies (pcs)	Standard Deviation (mm)		Weight (kg/m <sup>2</sup> )	Density avg. (kg/m <sup>3</sup> )
4	3	-0,5	+0,3	2,4	550-650**
6,5	5	-0,6	+0,4	3,9	
9	7	-0,7	+0,5	5,4	
12	9	-0,8	+0,6	7,2	
15	11	-0,9	+0,7	9	
18	13	-0,9	+0,7	10,8	
21	15	-1,0	+0,8	12,6	
24	17	-1,1	+0,9	14,4	
27	19	-1,8	+1,4	16,2	
30	21	-1,9	+1,5	18	
35	25	-1,5	+1,1	21	
40	27	-1,6	+1,2	24	
45	31	-1,8	+1,4	27	

\*Other thicknesses available upon request

\*\*As measured at 8-12% moisture content

### DIMENSIONAL DEVIATION AS PER EN 315 & EN 324

Length/Width	Deviation
< 1000 mm	± 1 mm
1000 – 2000 mm	± 2 mm
> 2000 mm	± 3 mm

### STRAIGHTNESS AND SQUARENESS DEVIATION AS PER EN 315 & EN 324

	Deviation
Straightness	± 0,1% or ± 1mm/m
Squareness	± 0,1% or ± 1mm/m

### RELEASE OF FORMALDEHYDE (EN 717-1)

½ E1

### BONDING QUALITY (EN 314-2)

Class 1  
Class 2  
Class 3

### MACHINING

Edge machining, CNC machining and drilling on request

### ADDITIONAL INFORMATION

1. General Terms of Sales available from [www.sklejkapaged.pl](http://www.sklejkapaged.pl)
2. Declaration of Performance available from [www.sklejkapaged.pl](http://www.sklejkapaged.pl)
3. Face veneer qualities according to EN 635-3.

Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.



Our product is made of renewable resource. Our products are characterized by low carbon footprint and are produced from certified wood, thus respecting the natural environment and the local community. The information contained in this document is intended as a guideline only and comes without warranty. We reserve the right to amend product specification sheets without notice.